

16: ALUMINIUM – INTERIOR BEHIND LININGS

page 1 of 3

DESCRIPTION

This system describes how the interior behind linings and bilges of an aluminium yacht may be coated with a two component epoxy system.

PRINCIPAL CHARACTERISTICS

This coating system may be applied directly to properly pre-treated aluminium and gives a excellent protection against corrosion. This system is scratch resistant and resistant to a wide range of chemicals, water and oil.

SURFACE CONDITION

Aluminium, in good condition.

SURFACE PREPARATION

New building

1. Remove all corrosion products, preferably by low pressure blasting with aluminium oxide or by sanding;
2. The surface should be dry and free from grease, loose particles and other contamination;
3. Apply as soon as possible the first coat of IJmopox ZF primer.

Maintenance

1. Clean the surface thoroughly to remove all contamination such as salt deposits, dirt, grease and other foreign matter, preferably by high pressure water cleaning and with a suitable cleaner;
2. Remove all corrosion products and paint layers with insufficient adhesion (including one component paints in good condition), preferably by low pressure blasting with aluminium oxide or by sanding;
3. Previous layers of two component paints which have good adhesion and which are in good condition should be abraded; preferably by low pressure blasting with aluminium oxide or by sanding;
4. Clean and dry the surface thoroughly;
5. Apply as soon as possible the first coat of IJmopox ZF primer.

MATERIALS AND SPREADING RATES

The following materials are used in this paint system:

IJmopox ZF primer	spreading rate approx. 0,10 l/m ²
Variopox Rolcoating	spreading rate approx. 0,15 l/m ² (solvent free system)
IJmopox HB coating	spreading rate approx. 0,22 l/m ² (high solids system)
IJmopox Verdunner	spreading rate depends on application method

APPLICATION

New building

1. Apply one coat of IJmopox ZF primer to a total dry film thickness of 50 µm (minimum spreading rate approx. 0,10 l/m²);
2. Apply one to two coats of Variopox Rolcoating to a total dry film thickness of 150 µm (minimum spreading rate approx. 0,15 l/m²);
3. As alternative for Variopox Rolcoating two coats of IJmopox HB coating may be applied instead to a total dry film thickness of 150 µm (minimum spreading rate approx. 0,22 l/m²). Variopox Rolcoating is free from any solvent and is preferred.

Maintenance, previously coated aluminium

1. Apply as spot-repair to damaged and bare areas one coat of IJmopox ZF primer to a total dry film thickness of 50 µm (minimum spreading rate approx. 0,10 l/m²);
2. Apply one to two coats of Variopox Rolcoating to a total dry film thickness of 150 µm (minimum spreading rate approx. 0,15 l/m²);

16: ALUMINIUM – INTERIOR BEHIND LININGS

page 2 of 3

3. As alternative for Variopox Rolcoating two coats of IJmopox HB coating may be applied instead to a total dry film thickness of 150 µm (minimum spreading rate approx. 0,22 l/m²). Variopox Rolcoating is free from any solvent and is preferred.

ADDITIONAL INFORMATION

- Properties of aluminium
To achieve good adhesion it is necessary to clean the surface thoroughly. Apply immediately after cleaning the first coat of IJmopox ZF primer.
- Previous paint: one or two component?
When it is not known if the previous coating system was based on one- or two component products, this can be determined with a simple test. Soak a small piece of cloth in Double Coat Ontvetter and leave this for 15 minutes on the surface. Remove the cloth and check the surface. When the previous paint has not dissolved, is not softened and cannot be easily removed it is most probably a two component paint. Only then it is possible to apply a fresh coat of two component paint.
- Bilges and anchor locker
This paint system is also suitable for bilges and anchor lockers. Bilges may be contaminated with oil residues therefore special attention should be given to the preparation of the surface.
- Durability and surface preparation
The durability of any paint system depends on a number of variables, amongst others: total dry film thickness, method of application, skill of labour, the conditions during which the coating is applied and cured, the exposure conditions during service and the preparation of the surface. Insufficient surface preparation might lead to blistering and loss of adhesion.
- Sanding
A durable adhesion will be obtained by thorough preparation of the surface. This may be achieved by sanding the surface. Sanding is also necessary when the time lapsed between application of each coat exceeds the maximum overcoating interval.
During application of the finishing coats, we recommend to use for each coat a finer grit paper. The table gives the recommended grit sizes:

Grit paper:	Recommended for:
P24 – P36	Suitable for steel prior to application of IJmopox ZF primer.
P60	Suitable for polyester gelcoat prior to the use of epoxy adhesives and bonding pastes.
P60 – P80	Suitable for: <ul style="list-style-type: none"> • Removal of old coats of paint, • Sanding aluminium prior to application of IJmopox ZF primer.
P120	Suitable for: <ul style="list-style-type: none"> • Sanding polyester gelcoat prior to repair with fillers, • Sanding of Variopox Injectiehars, Variopox Impregneerhars en Variopox Universele hars.
P120 – P180	Suitable for: <ul style="list-style-type: none"> • Wood, after application of first coat of paint, • Epoxy fillers, • Polyester fillers, • Sanding of IJmopox ZF primer and/or IJmopox HB coating between each coat.
P180 – P220	Suitable for: <ul style="list-style-type: none"> • Sanding of Variopox Injectiehars, Variopox Impregneerhars en Variopox Universele hars, • Sanding of IJmopox ZF primer of IJmopox HB coating prior to application of Double Coat.

16: ALUMINIUM – INTERIOR BEHIND LININGS

page 3 of 3

Grit paper:	Recommended for:
P220 – P280	Suitable for sanding gelcoat prior to application of Double Coat.
P320 – P400	Suitable for sanding Double Coat between each coat.
P600	Suitable for sanding Double Coat prior to application of the final coat Double Coat when dark colours are used such as DC 855, DC 854 en RAL 5011, etc.
Finer then P600	Suitable to remove dull areas prior to polishing.

- Example application schedule

Step		Dry film thickness (µm)	Spreading rate (m ² /l)	Recoating interval at 20 °C	Preparation before next step
1	Pre-treatment				
2	Apply first coat of IJmopox ZF primer	50	11.0	16 hours	When recoated within 72 hours no preparation is required, otherwise sanding with P180.
3	Apply first coat of Variopox Rolcoating	75	13.3	8 hours	
4	Apply second coat of Variopox Rolcoating	75	13.3	8 hours	Sanding P180.

- Relation dry/wet film thickness

Volume % IJmopox thinner	0	3	6	9	12
Wet film thickness IJmopox ZF primer at 50 µm dry film thickness	91	94	96	99	102
Wet film thickness IJmopox HB coating at 50 µm dry film thickness	71	74	76	78	80
Wet film thickness Variopox Rolcoating at 75 µm dry film thickness	75				

For detailed information on the products mentioned in this sheet, please refer to our technical information sheets.

Date: January 15

Disclaimer

Although the information and recommendations are presented in good faith and believed to be correct at date of issue, De IJssel Coatings B.V. makes no representations as of the completeness or accuracy thereof. In no event De IJssel Coatings B.V. will be responsible for damages of any nature whatsoever resulting from the use of this information. De IJssel Coatings B.V. reserves the right to change the information sheet without prior notifications. This information sheet supersedes any previous publications.